

SERIAL NO. _____
JUTTU, SMITH

PATENT APPLICATION
STC-02-0004 DIV

REMARKS

The Applicant respectfully requests entry of the above amendment and consideration of the application in view of the above amendment and the following remarks.

In the parent case, restriction was required between Claims 1-16, for a hydrocarbon conversion process, and Claims 17-47, for a catalyst, method of making a catalyst and a catalyst pretreatment. Claims 1-16 have been allowed.

On the basis of the above amendments and remarks, consideration of this application is requested and its allowance requested at the Examiner's earliest convenience. No new matter has been added.

Respectfully submitted,



Signature of Attorney

Jim Wheelington
Reg. No. 33,051

SABIC Americas, Inc.
SABIC Technology Center
1600 Industrial Blvd.
Sugar Land, Texas 77478
(281) 207-5719

SERIAL NO. _____
JUTTU, SMITH

PATENT APPLICATION
STC-02-0004 DIV

LISTING OF CLAIMS IN THE APPLICATION

1-16. Canceled.

17(Original). A process for synthesizing an aluminum-silicon-germanium-platinum zeolite catalyst comprising:

- a) preparing a zeolite containing aluminum, silicon and germanium;
- b) depositing platinum on the zeolite; and
- c) calcining the zeolite.

18(Original). The process of claim 17 wherein the platinum is deposited by cationic exchange.

19(Original). The process of claim 17 wherein the platinum is deposited by impregnation.

20(Original). The process of claim 17 wherein the zeolite has an MFI, FAU, TON, MFL, VPI, MEL, AEL, AFI, MWW or MOR structure.

21(Original). The process of claim 17 wherein the catalyst is subsequently treated first with hydrogen, second with a sulfur compound; and then again with hydrogen.

22(Original). An aluminum-silicon-germanium-platinum zeolite catalyst for aromatization of hydrocarbons comprising:

SERIAL NO. _____
JUTTU, SMITH

PATENT APPLICATION
STC-02-0004 DIV

- a) a microporous aluminum-silicon-germanium zeolite; and
- b) platinum deposited on the microporous aluminum-silicon-germanium-platinum.

23(Original). The catalyst of claim 22 wherein the silicon-germanium to aluminum atomic ratio is greater than 25:1.

24(Original). The catalyst of claim 22 wherein the silicon-germanium to aluminum atomic ratio in the range of from 45:1 to 250:1.

25(Original). The catalyst of claim 22 wherein the silicon-germanium to aluminum atomic ratio in the range of from 50:1 to 100:1.

26(Original). The catalyst of claim 22 wherein the silica to germania ratio is in the range of from 100:1 to 9:1.

27(Original). The catalyst of claim 22 wherein the silica to germania ratio is in the range of from 50:1 to 10:1.

28(Original). The catalyst of claim 22 wherein the silica to germania ratio is in the range of from 25:1 to 11:1.

SERIAL NO. _____
JUTTU, SMITH

PATENT APPLICATION
STC-02-0004 DIV

29(Original). The catalyst of claim 22 wherein platinum is present in the range of from 0.05% to 3%.

30(Original). The catalyst of claim 22 wherein platinum is present in the range of from 0.2% to 2%.

31(Original). The catalyst of claim 22 wherein platinum is present in the range of from 0.2% to 1.5%.

32(Original). The catalyst of claim 22 wherein the pore size of the zeolite is in the range from 5 to 100 angstroms.

33(Original). The catalyst of claim 32 wherein the pore size of the zeolite is in the range from 5 to 50 angstroms.

34(Original). The catalyst of claim 33 wherein the pore size of the zeolite is in the range from 5 to 20 angstroms.

35(Original). The catalyst of claim 22 wherein the zeolite has a MFI, FAU, TON, MFL, VPI, MEL, AEL, AFI, MWW or MOR structure.

36(Original). The catalyst of claim 22 wherein the catalyst additionally comprises a sulfur compound.

SERIAL NO. _____
JUTTU, SMITH

PATENT APPLICATION
STC-02-0004 DIV

37(Original). The catalyst of claim 36 wherein the sulfur compound is H_2S , $C_nH_{2n+2}S$ where $n = 1-20$, $C_nH_{2n+1}S_2$ where $n = 2-22$ or $C_nH_{2n+1}S$ where $n = 2-22$.

38(Original). The catalyst of claim 22 wherein the catalyst is represented by the formula $M[(SiO_2)(XO_2)_x(YO_2)_y]Z^{+}_{y/n}$ where M is a noble metal, X is a tetravalent element, Y is a trivalent element, Z is a cation with a valence of n, x varies from 0-0.15 and y is 0-0.125.

39(Original). The catalyst of claim 38 wherein M is platinum or gold.

40(Original). The catalyst of claim 38 wherein X is titanium, germanium or tin.

41(Original). The catalyst of claim 38 wherein Y is boron aluminum, gallium indium or tellurium.

42(Original). The catalyst of claim 38 wherein Z is H^+ , Na^+ , K^+ , Rb^+ , Cs^+ , Ca^{2+} , Mg^{2+} , Sr^{2+} or Ba^{2+} .

43(Original). The catalyst of claim 22 wherein the catalyst is of the formula $[H^+Pt][Si_{91}Ge_4Al_1O_{192}]-MFI$.

44(Original). The catalyst of claim 22 wherein its X-ray diffraction pattern includes the values given in Table 5 of this specification.

45(Original). A process for pretreating a catalyst for aromatization of hydrocarbons comprising:

- a) selecting an aluminum-silicon-germanium zeolite on which platinum has been deposited;
- b) treating the zeolite with hydrogen;
- d) treating the zeolite with a sulfur compound; and
- e) treating the zeolite a second time with hydrogen.

46(Original). The process of claim 45 wherein the zeolite is bonded with amorphous alumina prior to the first treatment step.

47(Original). The process of claim 45 wherein the sulfur compound is H_2S , $C_nH_{2n+2}S$ where $n = 1-20$, $C_nH_{2n+1}S_2$ where $n = 2-22$ or $C_nH_{2n+1}S$ where $n = 2-22$.